


Indestructible

specialist coatings manufacture



Pre-treatment	It is recommended that as a minimum the components to be coated should be solvent or alkali degreased whilst phosphating; chromating or fine shotblasting will increase performance and durability of the coating.
Curing Schedule	air dry or force cure 40 – 60 minutes at 60 – 70oC
Coverage	6-10 square metres per litre
Clean Up	Ipslip thinner 42000
Storage	Flammable Liquid; store and use in accordance with flammable liquid regulations
Health & Safety	Before use, refer to Product Safety Data Sheet



Indestructible Paint Ltd, 23-25 Pentos Drive, Sparkhill, Birmingham, B11 3TA, UK

Tel: +44 (0)121 702 2485 Fax: +44 (0)121 778 4338

www.indestructible.co.uksales@indestructible.co.uk

This information is given in good faith for guidance of users, but is without warranty or liability. Any queries should be referred to our technical department.